



MIRAPOXY WB (Water Based) EPOXY

PRODUCT DESCRIPTION

Miracote Mirapoxy WB is a two-component, superior, breathable, chemically resistant, water based epoxy floor coating system, which can be field-pigmented with ColorPax-W.

Miracote Mirapoxy WB Epoxy can be used as a primer, intermediate coating and topcoat, eliminating the confusion that multi-product applications can cause during installation. When used as a primer, it should be diluted one-to-one with potable water. When used as coating, it can be installed at full strength in two coats.

WHERE TO USE

Mirapoxy WB is an ideal concrete substrate coating system for use in commercial, institutional and light to moderate manufacturing environments.

Mirapoxy WB Epoxy is designed for rapid turn-around applications, where a tough and moderately chemical-resistant epoxy floor coating is desired.

It can be installed when high slab moisture content exists, including placement over "green-concrete" which is a minimum 7 days old and cured sufficiently for proper surface preparation, conditions that would prohibit the application of traditional epoxy coating and flooring systems. Mirapoxy WB complies with all Federal, State and Provisional VOC requirements.

ADVANTAGES

- Water-based, vapor permeable and breathable
- Rapid cure time, for quick return to service
- Can be applied over "green-concrete"
- VOC compliant
- Slip resistance enhancement with synthetic aggregate
- Recommended for interior application
- ADA Compliant, for in-situ validate ADA Compliance use a Variable Incident Tribometer Machine
- LEED (Leadership in Energy and Environmental Design) Credit Points may be available under 5 different Classifications
- Does not contain chemicals targeted by Green Seal Standard GS-11 and LEED-CS as unacceptable

For greater chemical resistance an optional finish coat can be employed, such as APU 100 clear or pigmented, which are chemical, abrasion and UV stable; or top coated with CR Topcoat, which is a novolac epoxy.

COVERAGE RATES

Wet: 400 sq. ft. per coat at 4 mils wet film thickness
Dry: 2 mil dft per coat

PACKAGING AND COLORS

7237-2GPA	Mirapoxy WB (A – 2 gallon pail)
7238-2GPB	Mirapoxy WB (B – 2 gallon pail)
7237-2GPA-S	Mirapoxy WB Satin (A – 2 gallon pail)
7238-2GPA-S	Mirapoxy WB Satin (B – 2 gallon pail)

Standard is Clear Gloss or Satin. For Color, use ColorPax-W – use two (2) ColorPax-W units per mixed 4 Gallons Mirapoxy WB. Always refer to Miracote ColorPax-E, U and W Color Chart

Also compatible with ColorPax-LIP units, but the color will not match the color chart because ColorPax-LIP are designed for use with white cement based products.

MIX RATIO

Mix ratio is 1A:1B by volume.

SHELF LIFE AND STORAGE

Shelf life will be one year from the date of manufacture as long as containers remain unopened and when material is store in a protected environment that is free from moisture, excessive heat and freezing temperatures, and direct sunlight.

TYPICAL PHYSICAL PROPERTIES @ 75°F (24°C)

Adhesion ASTM D4541	>400 psi
(100% failure in concrete)	(28.1 kg/cm)
Surface Hardness ASTM D2240 Shore D	50-60
Impact Resistance ASTM D2794	
(Direct, inch pound)	40
(Indirect, inch pound)	8
Water Absorption MIL-D-3134	< 1.0%
Abrasion Resistance ASTM D4060	
(CS17, 1000 gr load, 1000 cycles)	0.1 gr
Flammability ASTM D635	Self-Extinguishing
	Bonded to Concrete
Skid Resistance	Varies depending upon surface texture selected
Gloss Index (60°) ASTM 1544	80 to 90
Microbial Resistant ASTM G21	Passes Rating 1
Weight Solids (mixed components)	50.00%
Volume Solids (mixed components)	48.0%
Pot-Life	45-60 minutes
Tack-Free	60-90 minutes
Light Traffic	5-6 hours
Recoat Time	1-24 hours
Chemical Resistant	See Chemical Resistance Chart

OVERVIEW OF INSTALLATION STEPS

(Please refer to the following and contact Miracote with questions)

- **Surface Preparation** - Apply over a sound acceptable concrete substrate with a minimum CSP-4.
- **Mix** - Component A and Component B together, by slow to medium mixing paddle, 3 to 4 minutes per batch. Avoid introduction of air or deep vortex.
- **Application** - Prepare surface by careful and thorough removal of all laitance, grease, concrete curing agents and foreign matter.
 - Primer – Dilute one-to-one with clean potable water; 2 applications over porous fast absorbing substrate
 - 1st Coat – Apply uniformly with squeegee and back roll
 - 2nd Coat – Apply uniformly with squeegee and back roll
- **Finish** - Opaque with ColorPax -W Clear Gloss or Matte by roller, slight stipple or smooth.

NOTE: Moisture Mitigation: Also recommended for use where MVE, measured by ASTM F1869-04, exceeds 3.0 lbs/1000 ft² but is less than 10 lbs/1000 ft² per 24 hour period.



MIRAPOXY WB (Water Based) EPOXY

For Best Results:

Install a minimum 4' by 4' test area site mock up for approval of acceptable color, texture, finish, adhesion, and any other critical requirement acceptable to the owner prior to proceeding with the installation.

Verify current versions of product technical data sheets (PTDS), material safety data sheets (MSDS), and installation guidelines (IG) at www.miracote.com.

Protect materials from excessive heat and cold and regularly check wet film thickness with mil gauge and monitor consumption to ensure correct application thicknesses and rate are obtained.

LIMITATION

Do not apply over moving cracks, joints, or unsupported gaps. If sub-surface cracks after the coating is applied, the cracks will reflect through. Do not apply over working joints, expansion joints, or construction joints. The proper application of this product is the sole responsibility of the end user. Job site visits by Miracote representatives are a support service only and are not participatory in the quality or performance the contract. Supervision and quality control of work and contract are the sole responsibility of the contractor and user. Measure surface and ambient temperatures to assure application is within the acceptable range. If sub-surface cracks, the cracks may reflect through.

Application temperature – Slab and ambient temperature must be 40°F (4.5°C) and rising during placement and cure.

Not recommended for exterior application or areas subject to ultra violet light exposure. Application thickness is critical to cure and property development. Under application rate can result in retardation of cure and properties, over application can result in less than desired performance. Monitor application rate for best results.

PRODUCT AVAILABILITY

Crossfield Products Corp. maintains offices and/or factories at all addresses listed below. Products can be purchased through many building materials distributors.

MAINTENANCE

Depending on a number of various factors including weather conditions, location, UV exposure, vehicular vs. pedestrian traffic, your maintenance schedule will change. Please consult your local Miracote Representative for proper instructions. Acquire Care and Maintenance documents for this product from the manufacturer.

SPECIFICATION ASSISTANCE

Consult Crossfield Products Corp. for specification assistance, detailing, etc. This consultation is highly recommended prior to specification.

TESTING

The technical data contained herein is the result of tests made in Crossfield's laboratories or in independent laboratories using small scale equipment, following generally accepted trade practices. Although this information is believed to be true and accurate, the use of different equipment for testing under dissimilar conditions or the testing of samples produced under dissimilar conditions may develop substantially different results.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICES ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield's examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIAL NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



MIRACOTE PRODUCT LINE Crossfield Products Corp.

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA
90221
310-886-9100
310-886-9119 fax

East Coast Office
140 Valley Road
Roselle Park, NJ
07204
908-245-2800
908-245-0659 fax

www.miracote.com